

JIANGSU LANDISI WOOD CO., LTD

GUANHU TOWN, PIZHOU CITY, JIANGSU PROVINCE, CHINA

TEL: 008651686919777, FAX: 008651682896666 EMAIL: feiyawood7@feiyawood.com

TECHNICAL DATA SHEET

DATE: MAR 16, 2017


INVOICE NO.: LDSC170301

PRODUCT NAME: FILM FACED PLYWOOD (FFP)- CHINA, SUPERPLEX- IMPRINT IN GOLD ON BOTH SIDES BROWN FILM, MELAMINE GLUE, JPIC STANDARD-18MM- 13PLIES 11PLY+2FILM, BLUE COLOUR EDGES.

Technical Specifications					
Characteristics		Unit of Measure	Test Method	Value	Result
Moisture Content		%	En 322	10	Approved
Density		Kg/m3	En 323	600	Approved
Longitudinal Module of Elasticity		Mpa	En 310	6100	Approved
Lateral Module of Elasticity		Mpa		4800	Approved
Longitudinal Bending Strength(N/mm)		Mpa	En 310	55.01	Approved
Lateral Bending Strength(N/mm)		Mpa		43.01	Approved
Bonding	Bonding quality	Mpa	En 314	Max:1.72 Min:0.85	Approved
Data sheet of WBP(phenolic) GLUE					
Test item	Test result		starndard		
Appearance	Red Tansparent liquid		Red Tansparent liquid		
Solid content %	38.5%		30.8%~40.6%		
Viscosity cp	75		60~100		
Solid time sec	1020 s		900s~1200s		
PH	11		10~12		
Hydromete	1.089		1.018~1.198		

江苏兰蒂斯木业有限公司
JIANGSU LANDISI WOOD CO., LTD.

1.018~1.198




JIANGSU LANDISI WOOD CO., LTD

GUANHU TOWN, PIZHOU CITY, JIANGSU PROVINCE, CHINA

TEL: 008651686919777, FAX: 008651682896666 EMAIL: feiyawood7@feiyawood.com

MILL TEST CERTIFICATE

PRODUCT NAME: FILM FACED PLYWOOD (FFP)- CHINA			CONTRACT: UNITED TRADING & SUPPLY CO.		
			ITEM	THICKNESS	COLOR
TESTED DATE	MAR 16, 2017	FACE	1.10	B	
ORDER	UNITED TRADING & SUPPLY CO.	CORE	1.71	W	
STANDARD TEST	GB/T 17656-2008	CORE	1.66	B	
DIMENSION	18.0mmX4'X8''	CORE	1.70	W	
GLUE TYPE	WBP GLUE	CORE	1.75	B	
WOOD KIND	COMBI	CORE	1.70	W	
MOIST CONTENT	10.0%	CORE	1.75	B	
NUMBER OF SAMPLE	1	CORE	1.79	W	
SAMPLE TEST	1	CORE	1.66	B	
		CORE	1.75	W	
		BACK	1.17	B	
ITEM	UNIT	VALUE OF TEST		JUDGEMENT	
DENSITY	KG/M3	600		PASSED	
BONDING QUALITY	Mpa	0.85~1.72		PASSED	
	%	90%samples>=0.70Mpa		PASSED	
MODULES OF ELASTRICTY	Longitudinal	Mpa	6100	PASSED	
	Lateral		4800	PASSED	
BEND STRESS	Longitudinal	Mpa	55.01	PASSED	
	Lateral		43.01	PASSED	
REMARK:					
HOT PRESS: 930'					
TEMPERATURE : 135°C					
PRESS GAUCE: 10 kg/cm3					
DATE: MAR 16, 2017 ✓					
INVOICE NO.: LDSC170301					
VESSEL NAME: OCEAN APPLAUD 1703					
SHIPPING MARKS: UTSC&WOODWORLD					
 江苏三帝斯木业有限公司 JIANGSU LANDISI WOOD CO., LTD. VERY TRULY YOURS JIANGSU LANDISI WOOD CO., LTD					